

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- ✓ TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.


**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

CLAIMS:

1. A composition comprising

i) a thermoplastic polymer

5 ii) a compound having the formula




wherein R_1 , R_2 and R_3 are independently selected from an acyl group or a hydrogen atom,

wherein at least one of R_1 , R_2 and R_3 is an acyl group (a short acyl group) having from 2
10 to 6 carbon atoms

wherein at least one of R_1 , R_2 and R_3 is a branched chain acyl group (a long acyl group) consisting of a saturated chain having 10 to 20 carbon atoms and a hydrophilic branch group.

15 2. A composition according to claim 1 wherein the hydrophilic branch group is an acyl group or a derivative thereof.

3. A composition according to claim 2 wherein the hydrophilic branch group is a group of the formula



20

wherein p is from 0 to 4.

4. A composition according to any one of the preceding claims wherein two of R_1 , R_2 and R_3 are the short acyl groups and wherein the other of R_1 , R_2 and R_3 is a long acyl
25 group.

5. A composition according to any one of the preceding claims wherein the chain of the long acyl group consists of a chain having 14 to 20 carbon atoms.


6. A composition according to claim 5 wherein the chain of the long acyl group consists of a chain having 16 to 20 carbon atoms.
7. A composition according to any one of the preceding claims wherein the short
5 acyl group is an acyl group having from 2 to 5 carbon atoms.
8. A composition according to claim 7 wherein the short acyl group is an acyl group having 2 carbon atoms.
- 10 9. A composition according to any one of the preceding claims wherein the short acyl group is present in an amount, on average, of no greater than 2 moles per mole of glycerol and esters thereof.
- 15 10. A composition according to any one of the preceding claims wherein the long acyl group is present in an amount, on average, of at least 0.4 moles, preferably from 0.9 to 2 moles, more preferably from 0.9 to 1 moles per mole of glycerol and esters thereof.
- 20 11. A composition according to any one of the preceding claims wherein the total amount of the acyl groups is, on average, 2.7 to 3.0 moles per mole of glycerol and esters thereof.
- 25 12. A composition according to any one of the preceding claims wherein the compound is an acetylated interesterification product of glycerol and an oil selected from castor oil, including hardened castor oil, unhardened castor oil and mixtures thereof.
13. A composition according to any one of the preceding claims wherein the thermoplastic polymer is or comprises a vinyl chloride polymer or a vinyl chloride copolymer selected from vinyl chloride/vinyl acetate copolymer, vinyl chloride/vinylidene chloride copolymer, vinyl chloride/ethylene copolymer and a
30 copolymer prepared by grafting vinyl chloride onto ethylene/vinyl acetate copolymer, and mixtures thereof.

14. A composition according to any one of the preceding claims wherein the thermoplastic polymer is or comprises a polymer blend of a thermoplastic polymer and a second polymer.

5 15. A composition according to claim 14, wherein the second polymer is a methacryl polymer or an acrylonitrile-butadiene-styrene polymer.


16. A composition according to any one of the preceding claims wherein the composition comprises the compound in an amount of 1 to 100 parts by weight per 100
10 parts by weight of the thermoplastic polymer.

17. A composition according to any one of the preceding claims wherein the compound has the formula




15

18. A composition according to any one of claims 1 to 16 wherein the compound has the formula




20


19. A composition according to any one of claims 1 to 16 wherein the compound has the formula




20. A compound of the formula



5 wherein two of R_4 , R_5 , and R_6 are of the formula



wherein for each of the two of R_4 , R_5 , and R_6 q is independently selected from 0 to 3 and the other of R_4 , R_5 , and R_6 is a branched group of the formula



10 wherein n is from 10 to 20 and m is $2n$, and wherein p is from 0 to 4.

21. A compound according to claim 20 wherein p is from 0 to 3.


22. A compound according to claim 20 or 21 wherein q is 0.

15

23. A compound according to claim 20, 21 or 22 wherein n is from 16 to 20, preferably from 16 to 18, more preferably 17.


24. A compound according to any of claims 20 to 23 wherein the branched group is a

20 group of the formula




wherein x is from 7 to 10 and y is $2x$, and wherein p is from 0 to 4


25. A compound according to claim 24 wherein p is from 0 to 3.
26. A compound according to claim 24 or 25 wherein p is 0.
27. A compound according to claim 24, 25 or 26 wherein x is 10.
28. A compound of the formula




29. A compound of the formula



30. A compound of the formula



31. A composition comprising a compound as defined in any one of claims 20 to 30 and a thermoplastic polymer.
32. A process for the preparation of a compound having the formula




wherein R_1 , R_2 and R_3 are independently selected from an acyl group or a hydrogen atom,

wherein at least one of R_1 , R_2 and R_3 is an acyl group (a short acyl group) having from 2 to 6 carbon atoms; wherein at least one of R_1 , R_2 and R_3 is a branched chain acyl group (a long acyl group) consisting of a chain having 10 to 20 carbon atoms and a hydrophilic branch group;

the process comprising the steps of:

(i) interesterification between glycerol and triglyceride compound having the formula



10

wherein each of R_1 , R_2 and R_3 is a fatty acid group consisting of a chain having 10 to 20 carbon atoms, to provide a composition comprising glycerol, monoglyceride, diglyceride and/or triglyceride;

(ii) optionally isolating the monoglyceride and/or diglyceride from the composition;

15 (iii) acylating the monoglyceride and/or diglyceride or the composition containing the same.

33. A process according to claim 32 wherein the compound is a compound as defined in any one of claims 20 to 30.

20

34. A composition according to claim 1 as substantially hereinbefore described.

35. A compound according to claim 20 as substantially hereinbefore described.

25 36. A process according to claim 32 as substantially hereinbefore described.